

CI-005

Copper Inkjet Ink for TCO, ITO & Glass Substrates


A nanocopper-based ink for printed electronics

Product Overview

CI-005 is a nanosized metallic copper formulation, dispersed in a polymeric matrix suitable for high resolution inkjet printing

CI-005 is formulated to provide excellent conductivity and adhesion with glass, ITO & TCO coated glass

This ink can be used in a variety of printing equipment and can deliver drop sizes as low as 4 picolitres



Processing

Printing Equipment	Industrial ink jet print heads such as: Dimatix Sapphire, Konica Minolta KM512, Dimatix DMP2850 – 10 pL
Line resolution	As low as 50 μm @ 900 DPI (Depending on deposition equipment and DPI)
Line Thickness/Height (sintered)	~ 500 nm (Depending on drop volume)
Substrates	Soda lime glass, borosilicate glass, ITO & TCO coated glass.
Clean up solvent	Acetone, isopropanol
Surface Preparation	Clean & dry, no grease or contaminants (Plasma treatment can also be used)
Typical Drying Conditions	Can be dried in standard convection ovens and vacuum ovens @ 60°C, 30–60 minutes IR dryer @ 80°C, 15 minutes Forced air convection @ 80°C, 5–10 minutes
Typical Sintering Conditions	Laser sintering 808 nm – 1064 nm, Formic acid reducing atmosphere @ 250°C for 60 minutes dwell time

Applications

CI-005 ink is designed to be compatible with glass and coated glass to fabricate electronic circuitry common in rigid printed circuits.

Applications include:

- Touch screen
- Display
- Photovoltaic
- Sensors & Antennas

General Use, Storage and Shelf Life

The product should be kept sealed in its container and stored at room temperature (<25°C). The shelf life of unopened containers is six months from date of shipment.

Before use, please ensure that the ink is mixed thoroughly for a few minutes taking care to avoid introducing air to the ink. Filter the ink ($\leq 5 \mu\text{m}$ glass microfibre or nylon) prior to filling up the reservoir.

Safety and Handling

For safety and handling information relating to the use of this product, please refer to the Safety Data Sheet (SDS).

Technical Support

Intrinsiq works closely with its customers to ensure this product is optimized for their process. For more product information or technical support, please contact your local representative.

Intrinsiq Materials Ltd
Building Y25, Cody Technology Park
Ively Road, Farnborough
Hampshire, GU14 0LX
United Kingdom
Sales Tel: +44 (0)1252 396 238
+44 (0)7776 457 255

Email: ianclark@intqm.com

Typical Compositional properties

Solids content (Weight %)	26
Viscosity [cP] (Brookfield DVE @ 10 rpm, 20°C)	~13
Surface Tension [mN/m] (Static)	30
Density [g/ml]	1.27

Typical Electrical & Physical Properties (Sintered)

Bulk Resistivity [mΩ/cm]	~9
Adhesion (ASTM D3359)	5B

Intrinsiq Materials Inc
1200 Ridgeway Avenue
Rochester
NY 14615
USA
Sales Tel: +01 (585) 719 7107
+01 (619) 517 0710

Email dcufo@intqm.com